

# GCP Applied Technologies

## MONOKOTE Z-146 T Tunnel Test Reports

ASTM E859 Air Erosion	Page 2
ASTM E859 High Speed Air Erosion	Page 5
ASTM E937 Corrosion Test	Page 9
ASTM E759 Deflection	Page 13
ASTM E760 Bond Impact	Page 16
UL E84 Flame Spread Smoke Develop	Page 19



**AIR EROSION – ASTM E859-11**

**MONOKOTE® Z-146T**

**FIRE RESISTIVE MATERIAL**

**MADE FOR**

**GCP APPLIED TECHNOLOGIES INC.**

**CAMBRIDGE, MASSACHUSETTS**

**MADE BY**

**FROEHLING & ROBERTSON, INC.**

**GREENVILLE, SOUTH CAROLINA**

Copyright 2016 GCP Applied Technologies Inc.



## AIR EROSION TEST ABSTRACT

**Significance:** The Air Erosion Test measures the effect of a low speed air stream upon fire-resistive materials in plenums during normal service conditions, and evaluates the resistance to dusting, flaking, spalling and delamination of the fire-resistive material.

The test was conducted in accordance with ASTM E-859 “Air Erosion of Sprayed Fire-Resistive Materials Applied to Structural Members.”

**Results:** Monokote® Z-146T, when subjected to tangential air stream of a velocity of 20 ft./sec [6m/s], resulted in a weight loss of 0.000 grams at one hour, 0.000 grams during the next 5 hours, and 0.000 grams during the next 18 hours (24 hours test time), for a total weight loss of 0.000 grams over the 24 hour test period. The loss per area of test section for the total test period was 0.000 grams per square foot. The test density was 43.8 lbs./ft.<sup>3</sup> [701.6 Kg/m<sup>3</sup>].

## REPORT DETAILS

**Date of Test:** October 18, 2016 (sample preparation); November 15 and 16, 2016 (testing)

**Identification of Specimen:** Bags of Monokote® Z-146T were selected at random as produced by GCP Applied Technologies Inc. Each bag contained the label of Underwriters' Laboratories, Inc. Each bag of the Monokote® Z-146T was mixed with water in a mechanical mixer in accordance with the noted instructions to produce a uniform slurry having a mixer density of 54.8 pounds per cubic foot (pcf) and a nozzle density of 61.9 pcf. The procedures represented typical field construction practices and complied with the instructions printed on the Monokote® Z-146T bags.

### **Description of Test:**

#### I. Apparatus

- A. Application Base – 16 gauge galvanized sheet steel 14.5” x 67.5” [368 mm x 1715 mm].
- B. Duct System – A duct made of 12 gauge galvanized steel 8.7 feet long [2.64 meters], rectangular in cross section, with a 10.5” x 63.5” [267 mm x 1613 mm] opening in the top to accept the test sample (4.63 ft<sup>2</sup> or 0.430 m<sup>2</sup> exposed area).
- C. Blower – capable of moving air through the entire cross section of the duct at a velocity of 20 ft./sec [6 m/s].
- D. Pitot Tube – used in conjunction with a manometer to measure air velocity in the duct.
- E. Filters – one at the intake end of the duct (blower end) and a collecting filter at the exhaust end of the duct. Filter fabric was 30 denier nylon constructed with 94 ends per inch and 82 picks per inch.



II. Test Specimen:

The test specimen was a 16 gauge galvanized steel sheet 14.5" x 67.5" [368 mm x 1715 mm] onto which the Monokote® Z-146T was spray applied at 0.75" in thickness. The specimen as sprayed was allowed to cure and dry at laboratory conditions for a period of 28 days prior to testing.

III. Procedure:

- A. The collecting filter was dried for one hour at 120 °F [49 °C], weighed, and placed in the apparatus.
- B. The specimen was placed in the duct opening so that its face and the inside face of the duct opening were flush in the same plane. The specimen was sealed in place using silicone rubber adhesive. The edges overlapped the duct opening by 2 inches [50 mm].
- C. The pitot tube was positioned 4 inches [101 mm] from the upstream edge of the specimen at the center line of the duct, and 2 inches [50 mm] below the test specimen.
- D. With both filters in place, the blower was maintained at an average velocity of 20 ft./sec [6 m/s] throughout the duration of the test. The blower was stopped at intervals of 1, 6, and 24 hours. During this stoppage, the filter was removed, dried, and re-weighed to determine the mass gain.

IV. Results:

WEIGHING TIME	FILTER WEIGHT (g)	WEIGHT LOSS (g)	WEIGHT LOSS (g per ft <sup>2</sup> )
1 HR (initial)	1.444	0.000	0.000
1 HR (final)	1.444		
6 HR (initial)	1.451	0.000	0.000
6 HR (final))	1.451		
24 HR (initial)	1.464	0.000	0.000
24 HR (final)	1.464		

Monokote® Z-146T Density – 43.8 pcf

**Official Observers:**

Ryne Turner, PE - Froehling & Robertson, Inc.  
 Michael Morgan - GCP Applied Technologies Inc.

The data included in this report constitutes all the tests that were witnessed.

Respectfully submitted,

**FROEHLING & ROBERTSON, INC.**

Ryne Turner, PE  
 CMT Manager



**VERY HIGH SPEED**

**AIR EROSION TEST [100 MPH]**

**MONOKOTE TYPE Z-146T**

**FIRE RESISTIVE MATERIAL**

**MADE FOR**

**GRACE CONSTRUCTION PRODUCTS**

**GCP APPLIED TECHNOLOGIES INC. (FORMERLY W.R. GRACE & CO.)**

**TRAVELERS REST, SOUTH CAROLINA**

**MADE BY**

**FROEHLING & ROBERTSON, INC.**

**GREENVILLE, SOUTH CAROLINA**

**Copyright 1998 GCP Applied Technologies Inc. (formerly W.R. Grace & Co.)**



## AIR EROSION TEST

### ABSTRACT

**Significance:** This test measures the effect of a high speed air stream upon fire-resistive materials, and evaluates the resistance to dusting, flaking, spalling and delamination of the fire-resistive material.

The test was conducted in accordance with a modified version of ASTM E-859 "Air Erosion of Sprayed Fire-Resistive Materials Applied to Structural Members." Modifications were made to the duct system and therefore the sample size [see "Description of Test"] to achieve a higher velocity than described in the test method.

**Results:** Monokote Type Z-146T when subjected to tangential air stream of a velocity of 9,000 ft./min. or 102.2 m.p.h. [2,743 m/min. or 164.4 Km/hr.] resulted in a weight loss of 0.000 grams at one hour, 0.000 grams during the next 5 hours, and 0.000 grams during the next 18 hours (24 hours test time). The total weight loss was 0.000 grams per ft.<sup>2</sup> [0.000 grams per meter<sup>2</sup>] in 24 hours. The test density was 36.70 lbs./ft.<sup>3</sup> [588 Kg/m<sup>3</sup>].

### REPORT DETAILS

**Date of Test:** June 15, 1998

**Identification of Specimen:** Randomly selected of bags of Monokote Type Z-146T as produced by Grace Construction Products, GCP Applied Technologies Inc. (formerly W.R. Grace & Co.) were used. Each bag of Monokote Type Z-146T contained the label of Underwriters' Laboratories, Inc. Each bag of Monokote Type Z-146T was mixed with water in a mechanical mixer in accordance with the instructions on each bag of material to produce a cohesive uniform slurry having an average mixer density of 50.0 lbs./ft.<sup>3</sup> [801 Kg/m<sup>3</sup>] and a nozzle density of 55.4 lbs./ft.<sup>3</sup> [887 Kg/m<sup>3</sup>]. The procedures truly represented typical field construction practices and complied with the instructions printed on the Monokote Type Z-146T bags.

### Description of Test:

#### I. Apparatus

- A. Application Base - 12 gauge galvanized steel sheet 7.875 " by 65.5" [200 mm by 1664 mm].
- B. Duct System - A duct made of 12 gauge galvanized steel 69 inches long [1.75 meters], with a rectangular cross section of 3" by 6" [76 mm by 152 mm]. The duct had a 6" by 63.5" [152 mm by 1613 mm] opening at the top to accept the test sample. (2.65 ft.<sup>2</sup> or 0.246 m<sup>2</sup> exposed area).
- C. Blower - capable of moving air through the entire cross section of the duct at a velocity of 9,000 ft./min. or 102.2 m.p.h. [2,743 m/min. or 164.4 Km/hr.].
- D. Pitot Tube - used in conjunction with a manometer to measure air velocity in the duct.



- E. Filter - A collecting filter was attached at the exhaust end of the duct. Filter fabric was 30 denier nylon constructed with 94 ends per inch [25.4 mm] and 82 picks per inch [25.4 mm].
- F. Scale - balance having a capacity of 100 grams with sensitivity of  $\pm 0.001$  gram.

II. **Test Specimen:**

A. Substrate - 12 gauge galvanized steel sheet 7.875" by 65.5" [200 mm by 1664 mm] onto which the Monokote Type Z-146T was spray applied at 0.798 inch [ 20.3 mm] thickness. The specimen as sprayed was allowed to cure and dry at laboratory conditions. The test was conducted 221 days after application of the Monokote Type Z-146T.

- III. A. The collecting filter was dried for one hour at 120° F [49° C], weighed and placed in the apparatus.
- B. The specimen was placed into the duct opening so the face of the specimen and the inside face of the duct opening were flush and in the same plane and sealed in place using silicone rubber adhesive. The edges overlapped the duct opening by 1 inch [25.4 mm].
- C. The pitot tube was positioned in the center of the tube cross section at the upstream end of the test specimen.
- D. With the filter in place, the blower was maintained at an average velocity of 9,000 ft./min. or 102.2 m.p.h. [2,743 m/min. or 164.4 Km/hr.].
- E. The blower was stopped at intervals of 1, 6, and 24 hours, the collecting filter removed, dried, and re-weighed.

IV. **Test Data:**

- A. Density = 36.7 lbs./ft<sup>3</sup> [588 Kg/m<sup>3</sup>]
- B. Thickness tested = 0.798 inches [20.3 mm]
- C. Exposed area = 2.65 ft.<sup>2</sup> [0.246 m<sup>2</sup>]

Filter Weight (grams) at:	1 hour	6 hours	24 hours
Ending	3.823	3.832	3.800
Starting	3.823	3.832	3.800
Weight loss by sample	0.000	0.000	0.000
Total weight loss (24 hours) = 0.000 grams			
Total weight loss per ft. <sup>2</sup> = 0.000 grams [per m <sup>2</sup> = 0.000 grams]			



**Official Observers:**

Ken Huffman, Allen Ridenour - Froehling & Robertson, Inc.

Walter R. Payment - GCP Applied Technologies Inc. (formerly W.R. Grace & Co.)

The data included in this report constitutes all the tests that were witnessed.

Respectfully submitted,

FROEHLING & ROBERTSON, INC.

A handwritten signature in black ink, appearing to read 'R. Turner', is written over a horizontal line.

Ryne Turner, PE  
CMT Manager

*I certified this as an exact copy of the report generated by F&R in 1998*





**CORROSION TEST**

**MONOKOTE® TYPE Z-146T**

**FIRE RESISTIVE MATERIAL**

**MADE FOR**

**GCP APPLIED TECHNOLOGIES INC (FORMERLY W. R. GRACE & CO.)**

**CAMBRIDGE, MASSACHUSETTS**

**MADE BY**

**FROEHLING & ROBERTSON, INC.**

**GREENVILLE, SOUTH CAROLINA**

Copyright 2007 GCP Applied Technologies Inc (formerly W. R. Grace & Co.)



## CORROSION

### ABSTRACT

**Significance:** This test evaluates the corrosion to steel induced by sprayed fire-resistive materials and determines whether the presence of these materials increases, decreases, or had no effect on the corrosion characteristics of steel. The test was conducted in accordance with ASTM E-937 "Corrosion of Steel by Sprayed Fire-Resistive Material Applied to Structural Members".

**Results:** Monokote® Type Z-146T did not excessively contribute to corrosion of steel when exposed to higher temperature and humidity. Test density was 36.3 pounds per cubic foot (pcf) and the Monokote Z-146T thickness applied was 1 inch [25mm].

### REPORT DETAILS

**Dates of Testing:** January 26, 2007-February 5, 2007

**Identification of Specimen:** Bags of Monokote® Type Z-146T were selected at random as produced by GCP Applied Technologies Inc (formerly W. R. Grace & Co.). Each bag contained the label of Underwriters' Laboratories, Inc. The Monokote® Type Z-146T was mixed with water in a mechanical mixer in accordance with the instructions on each bag to produce a uniform slurry having an average mixer density of 48.0 pcf and a nozzle density of 57.0 pcf. The procedures represented typical field construction practices and complied with the instructions printed on the Monokote® Type Z-146T bags.

### Description of Test:

(1) Apparatus

- (a) An environmental chamber equipped to maintain the temperature at  $95 \pm 3$  °F and a relative humidity of  $95 \pm 3$  %.
- (b) Scale with a capacity of 2200 Kg and a sensitivity of  $\pm 0.1$  g.
- (c) Wire brush described as "cement mold brush" with brass wire bristles.

(2) Test Specimen:

Duplicate sets of 8" x 8" x 12 gauge sheets of galvanized (G60 grade), bare (A36 grade), and shop-coated steel (A36 grade) to which Monokote® Type Z-146T fire-resistive material was spray applied. The steel sheets were cleaned with Acetone to remove any oil or grease prior to material application. Two such sets of samples were prepared and tested on each type



of steel and the results were averaged. The shop coating was accomplished with a red iron oxide alkyd metal primer.

(3) Procedures:

- (a) Prior to the application of Monokote® Type Z-146T, the duplicate sheets were weighed to the nearest 0.1 gram and identified as I<sub>a</sub> and II<sub>a</sub>. The backs (unsprayed sides) of the plates were coated with wax.
- (b) After the application of Monokote® Type Z-146T, specimens marked I<sub>a</sub> were dried to constant weight at laboratory conditions [68 ± 9 °F with relative humidity not greater than 60%].
- (c) Specimens marked II<sub>a</sub> were placed into the chamber and kept at 95 ± 3°F and 95% ± 3% relative humidity for 240 hours.
- (d) After this exposure, the fire-resistive material and protective wax were removed. All surface rust was removed with the wire brush. The cleaned sheets were then weighed to the nearest 0.1 gram and identified as II<sub>b</sub>.
- (e) The control specimens (those not exposed to higher temperature and humidity) were then cleaned and weighed in the same manner as the conditioned specimens and marked as I<sub>b</sub>.

(4) Calculations: The difference in weight loss between the Control and the Conditioned specimens is expressed in grams per square millimeters of surface area as follows:

$$L_{II} = (II_a - II_b)/A_{II} \quad L_I = (I_a - I_b)/A_I \quad \text{and} \quad D = L_{II} - L_I$$

Where:

- L<sub>I</sub> = loss at end of initial (Control) aging period in g/mm<sup>2</sup>
- L<sub>II</sub> = loss at end of the Conditioned (240 hr) period in g/mm<sup>2</sup>
- D = difference in weight loss in g/mm<sup>2</sup>
- I<sub>a</sub> = original weight of steel plate I in grams
- I<sub>b</sub> = weight of steel plate I in grams after cleaning off SFRM and any rust
- II<sub>a</sub> = original weight of steel plate II in grams
- II<sub>b</sub> = weight of steel plate II in grams after cleaning off SFRM and any rust
- A<sub>I</sub> = area of steel plate I in mm<sup>2</sup>
- A<sub>II</sub> = area of steel plate II in mm<sup>2</sup>



**TEST DATA:**

STEEL TYPE	CONTROL		Diff. I <sub>a</sub> -I <sub>b</sub>	CONDITIONED		Diff. II <sub>a</sub> -II <sub>b</sub>
	I <sub>a</sub>	I <sub>b</sub>		II <sub>a</sub>	II <sub>b</sub>	
Bare (1)	950.6	950.6	0.0	839.5	839.5	0.0
Bare (2)	841.0	841.0	0.0	965.6	965.6	0.0
Shop Coated (1)	847.7	847.7	0.0	831.2	831.2	0.0
Shop Coated (2)	953.3	953.3	0.0	844.2	844.2	0.0
Galvanized (1)	957.7	957.7	0.0	842.3	842.3	0.0
Galvanized (2)	961.5	961.5	0.0	838.8	838.8	0.0

Monokote® Type Z-146T Thickness = 1.0 inches

Density = 36.3 pcf

**RESULTS:** (Average of two tests)

Weight loss of control specimens : (I<sub>a</sub>-I<sub>b</sub>)

Bare Steel = 0.0 grams      Shop Coated Steel = 0.0 grams  
Galvanized Steel = 0.0 grams

Weight loss of conditioned specimens: (II<sub>a</sub> - II<sub>b</sub>)

Bare Steel = 0.0 grams      Shop Coated Steel = 0.0 grams  
Galvanized Steel = 0.0 grams

Difference in weight loss: (II<sub>a</sub> - II<sub>b</sub>) - (I<sub>a</sub> - I<sub>b</sub>)      Grams/mm<sup>2</sup>

Bare Steel                    =      0.0 grams                    0  
Shop Coated Steel        =      0.0 grams                    0  
Galvanized Steel           =      0.0 grams                    0

**Official Observers:**

David Knowles, PE - Froehling & Robertson, Inc.  
Doug Macy - GCP Applied Technologies Inc (formerly W. R. Grace & Co.)  
Karl D. Taub - GCP Applied Technologies Inc (formerly W. R. Grace & Co.)

The data included in this report constitutes all the tests that were witnessed.

Respectfully submitted,

**FROEHLING & ROBERTSON, INC.**

Ryne Turner, PE  
Branch Manager

DocuSign

*I certified this as an exact copy of the report generated by F&R in 2007*



**DEFLECTION TEST – ASTM E759-11**

**MONOKOTE® Z-146T**

**FIRE RESISTIVE MATERIAL**

**MADE FOR**

**GCP APPLIED TECHNOLOGIES INC.**

**CAMBRIDGE, MASSACHUSETTS**

**MADE BY**

**FROEHLING & ROBERTSON, INC.**

**GREENVILLE, SOUTH CAROLINA**

Copyright 2016 GCP Applied Technologies Inc.



## DEFLECTION TEST ABSTRACT

**Significance:** The Deflection Test measures the behavior of sprayed fire-resistive materials when the floor construction to which it is applied is subjected to deflection and evaluates such phenomena as spalling and delamination under bending stress. It is an indication of the ability of the sprayed fire-resistive material to remain in place and resist removal during anticipated service conditions.

The test was conducted in accordance with ASTM E-759-11 "Effect of Deflection on Sprayed Fire-Resistive Materials Applied to Structural Members."

**Results:** Monokote® Z-146T did not crack, spall, or delaminate and remained unchanged in every aspect when the backing to which it was applied was subjected to deflection of 1/120<sup>th</sup> of the span. The test density was 43.8 lbs./ft.<sup>3</sup> [701.6 Kg/m<sup>3</sup>].

### REPORT DETAILS

**Date of Test:** October 18, 2016 (sample preparation); November 15, 2016 (testing)

**Identification of Specimen:** Bags of Monokote® Z-146T were selected at random as produced by GCP Applied Technologies Inc. Each bag contained the label of Underwriters' Laboratories, Inc. Each bag of the Monokote® Z-146T was mixed with water in a mechanical mixer in accordance with the noted instructions to produce a uniform slurry having a mixer density of 54.8 pounds per cubic foot (pcf) and a nozzle density of 61.6 pcf. The procedures represented typical field construction practices and complied with the instructions printed on the Monokote® Z-146T bags.

#### Description of Test:

##### I. Apparatus

- A. Supports - A rigid base to provide 4 inches [101 mm] bearing and a clear span between supports of 10 feet [3.05 meters].
- B. Load - Pre-weighed bars of iron.
- C. Deflection Gauge - a dial micrometer graduated to 0.001 inch [0.25 mm].

##### II. Test Specimen:

The test specimen was a cellular steel deck of non-composite type, nominal 1.5 inches deep, 24 inches wide by 12 feet long [38 mm x 610 mm x 3.66 meters], consisting of an 18 gauge galvanized steel fluted top section and a 20 gauge steel flat bottom section welded together to form four cells 6 inches [152 mm] on center. The fire-resistive material was then spray applied to the underside of the steel deck to a 3/4 inch [19 mm] thickness. The Monokote® Z-146T was not applied to an area 12 inches [305 mm] from each end of the specimen in order to permit the steel deck to bear directly on the supports of the test fixture.



III. Procedure:

The prepared specimen was allowed to condition at atmospheric conditions for a period of 35 days prior to testing. The test specimen was placed on the test fixture supports to simulate field conditions of a floor construction with sprayed Monokote® Z-146T fire-resistive material as the lower surface. The specimen had a clear span between supports of 10 feet [3.05 meters]. A vertical load was applied to the upper face of the specimen to develop a deflection of 1/120 of the clear span, or 1.0 inch [25.4 mm]. To measure the deflection, the initial reading of the dial micrometer was recorded prior to the application of the load, and deformation monitored as the load was applied.

IV. Results:

The test specimen was examined upon completion of the test. No evidence of cracking, spalling, delamination, loss of bond or any other change in the Monokote® Z-146T was observed after being subjected to the above described test procedure

**Official Observers:**

Ryne Turner, PE - Froehling & Robertson, Inc.

Michael Morgan - GCP Applied Technologies Inc.

The data included in this report constitutes all the tests that were witnessed.

Respectfully submitted,

**FROEHLING & ROBERTSON, INC.**

Ryne Turner, PE  
CMT Manager



**BOND IMPACT TEST – ASTM E760-11**

**MONOKOTE® Z-146T**

**FIRE RESISTIVE MATERIAL**

**MADE FOR**

**GCP APPLIED TECHNOLOGIES INC.**

**CAMBRIDGE, MASSACHUSETTS**

**MADE BY**

**FROEHLING & ROBERTSON, INC.**

**GREENVILLE, SOUTH CAROLINA**

Copyright 2016 GCP Applied Technologies Inc.





## BOND IMPACT TEST ABSTRACT

**Significance:** The Bond Impact Test measures the behavior of sprayed fire-resistive materials when the floor construction to which it is applied is subjected to the impact of shock loading, and evaluates adhesion and resistance to spalling, cracking, and delamination. It is an indication of the ability of the sprayed fire-resistive material to remain in place and resist removal during anticipated service conditions.

The test was conducted in accordance with ASTM E-760-11 “Effect of Impact on Bonding of Sprayed Fire-Resistive Materials Applied to Structural Members.”

**Results:** Monokote® Z-146T did not crack, spall, or delaminate and remained unchanged in every aspect when the floor construction to which it was applied was subjected to an impact shock loading of 240 foot-pounds (60 pounds dropped from 4 feet), or 33 Kilogram-meters (27.2 Kilograms dropped from 1.2 meters). The test density was 43.8 lbs./ft.<sup>3</sup> [701.6 Kg/m<sup>3</sup>].

## REPORT DETAILS

**Date of Test:** October 18, 2016 (sample preparation); November 15, 2016 (testing)

**Identification of Specimen:** Bags of Monokote® Z-146T were selected at random as produced by GCP Applied Technologies Inc. Each bag contained the label of Underwriters' Laboratories, Inc. Each bag of the Monokote® Z-146T was mixed with water in a mechanical mixer in accordance with the noted instructions to produce a uniform slurry having a mixer density of 54.8 pounds per cubic foot (pcf) and a nozzle density of 61.9 pcf. The procedures represented typical field construction practices and complied with the instructions printed on the Monokote® Z-146T bags.

### **Description of Test:**

#### I. Apparatus

- A. Supports – a rigid base to provide 4 inches [101 mm] bearing and a clear span between supports of 10 feet [3.05 meters].
- B. Impact Instrument – a steel-shot filled leather bag weighing 60 lbs. (27.2 kg).
- C. Measuring Stick – used to accurately measure the height of drop.

#### II. Test Specimen:

The test specimen consisted of a complete deck assembly of a cellular steel deck and a concrete topping. The cellular steel deck was of the non-composite type, nominal 1.5 inches



deep, 24 inches wide by 12 feet long [38 mm x 610 mm x 3.66 meters], consisting of an 18 gauge galvanized steel fluted top section and a 20 gauge steel flat bottom section welded together to form four cells 6 inches [152 mm] on center. The concrete was nominal 3,000 psi [211 Kg/cm<sup>2</sup>] mix, poured 2.5 inches deep [63 mm] as measured to the top plane of the steel decking. The Monokote® Z-146T fire-resistive material was then spray applied to the underside of the steel deck to a 3/4 inch [19 mm] thickness. The Monokote® Z-146T was not applied to an area 12 inches [305 mm] from each end of the specimen in order to permit the steel deck to bear directly on the supports of the test fixture.

III. Procedure:

The prepared specimen was allowed to condition at atmospheric conditions for a period of 28 days prior to testing. The test specimen was placed on the fixture supports to simulate field conditions of a floor construction with sprayed Monokote® Z-146T fire-resistive material as the lower surface and the concrete as the upper surface. The specimen had a clear span between supports of 10 feet [3.05 meters]. An impact load was applied to the upper face of the specimen by dropping the instrument from a height of 4 feet [1.22 meters]. The height of the bag was measured from the upper face of the specimen prior to release.

IV. Results:

The test specimen was examined upon completion of the test. No evidence of cracking, spalling, delamination, loss of bond or any other change in the Monokote® Z-146T was observed after being subjected to the above described test procedure

**Official Observers:**

Ryne Turner, PE - Froehling & Robertson, Inc.

Michael Morgan - GCP Applied Technologies Inc.

The data included in this report constitutes all the tests that were witnessed.

Respectfully submitted,

**FROEHLING & ROBERTSON, INC.**

Ryne Turner, PE  
CMT Manager



**BLPR.R4339  
Cementitious Cement and Plaster Mixtures**

[Page Bottom](#)

**Cementitious Cement and Plaster Mixtures**

[See General Information for Cementitious Cement and Plaster Mixtures](#)

**GCP APPLIED TECHNOLOGIES INC**

R4339

FIRE OPERATING UNIT  
62 WHITTEMORE AVE  
CAMBRIDGE, MA 02140 USA

Cementitious mixtures applied to inorganic reinforced cement board and/or foamed plastic.

**Applied To Inorganic Reinforced Cement Board**

	MK-4	MK-5	RG	Type 105	KM-106
Flame Spread	10	10	0	0	0
Smoke Developed	0	0	0	0	0

	Z-3306G	MK-6/HY or MK-6/HB or MK-10/HB or MK-10/HB ES or MK-6/HY ES	Z-106/HY	MK-6 GF or MK-6 GF Extended Set	MK-6s or Z-106G or MK-1000/HB or MK-1000/HB Extended Set	AK-1
Flame Spread	0	0	5	0	0	0
Smoke Developed	0	0	0	0	0	0

	Type 105	Type Z-106	Type KM-601	Type Z-146, Z-146 NPP, Z-146PC, Z-146T, Z-156, Z-156PC, Z-156T	Monokote Acoustic 1	Monokote Acoustic 5	Monokote Acoustic 35
Flame spread	0	0	0	0	0	0	0
Smoke developed	0	0	0	0	0	0	0

	Applied to Inorganic Reinforced Cement Board in a Max Thk of 1 In. Type Z-3300TB+, ++
Flame Spread	5
Smoke Developed	0

	Applied to Inorganic Reinforced Cement Board In a Max Thk of 1/2 in. Type Z-Acoustical Plaster
Flame Spread	0
Smoke Developed	0

+ FOR SURFACE BURNING CHARACTERISTICS APPLIED OVER FOAMED PLASTIC, SEE CLASSIFICATION MARKING OF UNDERWRITERS LABORATORIES INC. ON PRODUCT OR CARTON.

++ Systems utilizing cementitious mixture covering over 2 in. thickness of foamed plastic, fire tested in accordance with the International Conference of Building Officials Research Committee Acceptance Criteria for Foam Plastics under Section 1717 (b) of the 1976 Uniform Building Code.

	Applied Over 2 In. Thk Foamed Plastic
Flame Spread	0
Smoke Developed	0

	<b>In. a Min Thkns of 1/2 In. Type Z-3300TB††</b>
Flame spread	10
Smoke developed	0

\* A Foamed plastic formed by the simultaneous spraying of two liquid components (CPR-485, Component "A" and CPR-485, Component "B" ) as manufactured by The Upjohn Company, CPR Division. This foamed plastic has values of Over 200 for flame spread, 15 for fuel contributed and Over 500 for smoke developed.

\* A1 Systems utilizing 3/4 in. thick cementitious mixture covering over 2 in. thickness of foamed plastic, fire tested in accordance with the Uniform Building Code Standard 26-3.

	<b>Applied Over 2 In. Thk Foamed Plastic * In. a Min Thkns of 1/2 in. Type Z3300TB*</b>
Flame spread	5
Smoke developed	0

\* Foamed plastic in the form of boards identified as Type B and manufactured by GCP Applied Technologies Inc. and bearing the Fire Hazard Classification Marking of Underwriters Laboratories Inc. The 2 in. thickness of foamed plastic exhibited values of 5 for flame spread, not determinable for fuel contributed, and 40 for smoke developed, while material remained in original test position; ignition of molten residue on the furnace floor resulted in flame travel equivalent to calculated Flame Spread Classification of 100 and Smoke Developed Classification of Over 500.

\*\* A system utilizing 1/2 in. thickness of cementitious mixture covering 2 in. thickness of foamed plastic,thickness of foamed plastic.

**FOR SURFACE BURNING CHARACTERISTICS SEE CLASSIFICATION MARK  
OF UL ON PRODUCT OR CARTON**

Last Updated on 2016-09-23

[Questions?](#)

[Print this page](#)

[Terms of Use](#)

[Page Top](#)

© 2016 UL LLC

The appearance of a company's name or product in this database does not in itself assure that products so identified have been manufactured under UL's Follow-Up Service. Only those products bearing the UL Mark should be considered to be Certified and covered under UL's Follow-Up Service. Always look for the Mark on the product.

UL permits the reproduction of the material contained in the Online Certification Directory subject to the following conditions: 1. The Guide Information, Assemblies, Constructions, Designs, Systems, and/or Certifications (files) must be presented in their entirety and in a non-misleading manner, without any manipulation of the data (or drawings). 2. The statement "Reprinted from the Online Certifications Directory with permission from UL" must appear adjacent to the extracted material. In addition, the reprinted material must include a copyright notice in the following format: "© 2016 UL LLC".