

FORCE 10,000[®] D Data Sheet

High performance concrete admixture dry densified powder

Product Description

FORCE 10,000[®]D is a dry densified microsilica (silica fume) powder designed to increase concrete compressive and flexural strengths, increase durability, reduce permeability and improve hydraulic abrasion-erosion resistance. The specific gravity of FORCE 10,000[®]D is 2.20.

Uses

FORCE 10,000[®]D can be used to consistently produce concrete with strengths of 6,000 psi (42 MPa) and higher in most instances with locally available materials and existing methods. It may also be used in precast and prestress applications where high early strengths are required.

The addition of FORCE 10,000[®]D also produces concrete with increased watertightness and dramatically reduced permeability compared to conventional mixes. Reduced permeability is an important advantage in slowing the intrusion of chloride where corrosion of reinforcing steel is a potential problem. Examples are parking garages, bridge decks and concrete in a marine environment. FORCE 10,000[®]D also enhances the durability of concrete against aggressive chemical attack and in hydraulic abrasion-erosion applications.

Preconstruction Trial Mix

It is strongly recommended that trial mixes be made several weeks before construction start up. This will allow the concrete producer an opportunity to determine the proper batching sequence and amounts of other admixtures needed in order to deliver the required concrete mix to the job site. A trial mix will also help determine whether the combination of concrete materials and construction practices will allow the concrete to meet a specified performance. GCP's broad experience with this product can help the concrete producer deliver a satisfactory product regardless of the mixture proportions. Contact your GCP Applied Technologies sales representative for help with trial mixes.

Finishing & Curing

FORCE 10,000[®]D concrete can be used in flatwork with little or no modification to the recommended practices outlined in ACI 302, *Guide for Concrete Floor and Slab Construction*.

FORCE 10,000[®]D will reduce the surface bleed water of concrete in large applications. ACI 308, *Standard Practice for Curing Concrete*, must be followed to ensure that any problems that can occur due to decreased bleeding are minimized. Your GCP Applied Technologies representative is available to review your particular job needs.

Performance

FORCE 10,000[®]D improves concrete through two mechanisms. The extremely fine microsilica particles are able to fill the microscopic voids between the cement particles, creating a less permeable structure. In addition, the microsilica reacts with the free calcium hydroxide within the concrete to form additional calcium silicate hydrate (glue), producing a tighter paste-to-aggregate bond. FORCE 10,000[®]D does not affect concrete set times.

FORCE 10,000[®]D will improve the mechanical properties of concrete. In order to meet specified concrete performance levels, however, many variables are involved. These include, but are not limited to; concrete materials, weather conditions, testing techniques and mixing, transporting, placing and finishing practices. ACI and ASTM guidelines must be strictly adhered to.

Addition Rates

FORCE 10,000[®]D dosage rates will vary based on the requirements of the application. Dosage rates should be calculated on percent microsilica by weight of cement, or on lb/yd³ (kg/m³) of concrete, as appropriate. Dosage rates will be as specified. If not specified, consult your GCP Applied Technologies representative for your particular job needs.

Compatibility with Other Admixtures and Batch Sequencing

FORCE 10,000[®]D is compatible with all conventional water reducers, superplasticizers, set retarders and DCI[®] corrosion inhibitor. Any air-entraining agent which works effectively with superplasticizers and microsilica, particularly vinsol resins such as DARAVAIR[®] by GCP Applied Technologies, are recommended. Only non-chloride set accelerators, such as POLARSET[®], may be used with FORCE 10,000[®]D concrete. All admixtures must be added separately to assure their prescribed performance. Trial mixes and pretesting of concrete are recommended to optimize dosage rates, and ensure ultimate performance.

FORCE 10,000[®]10,000 D can be used in either central or transit mix concrete production. FORCE 10,000[®]D may be used in conjunction with waterreducing admixtures (both normal and high-range as approved by ASTM) to assure workability of the mix.

Packaging, Handling and Storage

FORCE 10,000[®]D is available in bulk, and 25 lbs (11.4 kg) Concrete Ready Bags[™].

Bagged FORCE 10,000[®]D should be stored in a dry, protected area. Manual dispensing by tearing the bags is the normal method. A dust mask should be used when dispensing the bagged product, consult the product MSDS for more complete instructions.

Dispensing Equipment

Bulk FORCE 10,000[®]D may be stored in already existing cement silos. The silos must be completely clean with no foreign residue remaining which may cause contamination. Up-pipes to the silo for unloading bulk tankers should also be clean and clear of obstructions. Small diameter 4 in. (100 mm) rigid metal pipes with several angles (especially right angles) will cause longer unloading times. Large diameter 6 in. (150 mm) flat lined, flexible rubber pipes will allow for the least unloading time. Dispensing bulk FORCE 10,000[®]D will take place in the same manner as that used for cement. Augering or dropping from the silo to the weigh hopper is the usual practice.

gcpat.com | North America Customer Service: +1 (877) 423 6491

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

FORCE 10,000, DCI, DARAVAIR, and POLARSET are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Suite 400, Alpharetta, GA 30009, USA

GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6

This document is only current as of the last updated date stated below and is valid only for use in the United States. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2023-06-28

gcpat.com/solutions/products/force-10000-d-silica-fume/force-10000-d-data-sheet