

TB-0901 — Offset the Potential Corrosive Effect of Chlorides in a Concrete Mix Using DCI® Technical Bulletin

/ concrete / mix design

DCI®Corrosion Inhibitor may be used to offset the corrosive effects of chloride ions found in steel reinforced concrete. Chloride ions in the form of salts may combine with oxygen and moisture in concrete and corrode the embedded steel. Chloride ions are present at varying levels in almost all aggregate and water sources; consequently, all concrete contains some chloride ions. The American Concrete Institute has established levels of acceptable chloride ions in concrete based upon service conditions.

The table below contains the recommendation of ACI 318 “Building Code Requirements for Structural Concrete.” In some cases, the aggregates and mix water contribute levels of chloride ions to the concrete that exceed ACI limits. In these instances DCI®Corrosion Inhibitor may be added to the concrete mix to counteract the detrimental effects of the chloride ions. The use of DCI® may be far less expensive to the concrete producer than finding alternate sources of materials. Technically, the producer may still be in violation of ACI maximum chloride limits, but DCI®will counteract the potential corrosive effects of these unwanted chlorides so the producer and specifying engineer may allow its usage. In order to determine how much DCI®to use, the concrete must be tested for water-soluble chloride ion content. After the chloride content is measured, the DCI®dosage rate may be taken from the table below.

DCI® Dosage Recommendations

Water Soluble Chloride Ion Content (lbs/yd ³)	DCI® Dosage (gal/yd ³)
0.00–0.50	0.50
0.51–0.75	0.75
0.76–1.00	1.00
1.01–1.25	1.25
1.26–1.50	1.50
1.51–1.75	1.75
1.76–2.00	2.00

Example: A prestressed concrete producer using a 705 lb cement factor mix tests for chloride content and finds that the mix contains 0.85 lb of chloride ions per cubic yard, or 0.12% by weight of cement. The chloride content percentage exceeds the ACI limit and the producer and the design engineer agree to use DCI®to protect the embedded steel from corrosion. Locating 0.85 lb of chlorides per cubic yard on the table, 1.0 gallon of DCI®per cubic yard is recommended.

gcpat.com | North America Customer Service: +1 (877) 423 6491

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

DCI is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

In Canada, 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Suite 475, Alpharetta, GA 30009, USA

GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6

This document is only current as of the last updated date stated below and is valid only for use in the United States. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2024-06-21

gcpat.com/solutions/products/dci-corrosion-inhibitor/tb-0901-offset-potential-corrosive-effect-chlorides-a