

# TB-0708 — Shrinkage Characteristics of FORCE 10,000® Concrete Technical Bulletin

/ concrete / mix design

## Introduction

FORCE 10,000® concrete is typically used in applications where cracking may be a major concern. These include environments that are highly corrosive, chemically saturated, or very abrasive and where less permeable, more durable concrete is required. For these applications concrete needs to be designed and constructed to produce the least amount of cracking.

A series of tests was conducted by GCP Applied Technologies to examine the shrinkage characteristics of FORCE 10,000® concrete as it relates to aggregates, plain concrete and length of curing. The evaluations included several mix designs with silica fume dosage rates ranging from 0 to 10.8% by weight of cement. The concrete was sampled, prepared, cured and tested in accordance with ASTM C157, “Length Change of Hydraulic Cement Concrete.”

**Test Series 1: The Effect of Aggregate Type on Shrinkage of Force 10,000 Concrete**

Coarse Aggregate Type	River Gravel		Crushed Limestone	
Coarse aggregate	1090 kg	1837 lbs	1051 kg	1771 lbs
Type II cement	332 kg	560 lbs	332 kg	560 lbs
Class F fly ash	59 kg	100 lbs	59 kg	100 lbs
Force 10,000	42.4 kg	71.5 lbs	42.4 kg	71.5 lbs
HRWR	1174 mL/100 kg	18 oz/100 lbs	1174 mL/100 kg	18 oz/100 lbs
W/C + P ratio	0.35	0.35		
Slump	102 mm	4 in.	102 mm	4 in.
Air content, %	2.0		2.0	
% Length change, shrinkage, drying age (after 7 days wet cure)	River Gravel		Crushed Limestone	
7 days	0.040		0.025	
28 days	0.078		0.038	
56 days	0.080		0.035	
90 days	0.075		0.036	

Note: Values do not represent all limestone and gravel aggregates.

**Test Series 2: The Effect of Force 10,000 on Shrinkage at Equal Paste Content**

Mix Description	with Force 10,000		without Force 10,000	
Units	SI	US	SI	US
Type II cement	332 kg	560 lbs	392 kg	600 lbs
Class F fly ash	59 kg	100 lbs	59 kg	100 lbs
Force 10,000	42.4 kg	71.5 lbs	0 kg	0 lbs
HRWR	1174 mL/100 kg	18 oz/100 lbs	1174 mL/100 kg	18 oz/100 lbs
W/C + P ratio	0.35	0.34		
Slump	127 mm	5 in.	127 mm	5 in.
Air content, %	3.0		3.0	
% Length change, shrinkage, drying age (after 7 days wet cure)	with Force 10,000		without Force 10,000	
7 days	0.040		0.038	
28 days	0.078		0.075	
56 days	0.080		0.079	
90 days	0.075		0.076	

Test Series 3: The Effect of Curing on Shrinkage of Force 10,000 Concrete

Mix Description	Midwest Gravel	Northeast Gravel	Midwest Limestone
W/C + P ratio	0.37	0.37	0.37
Force 10,000	27.2 kg (46 lbs)	27.2 kg (46 lbs)	27.2 kg (46 lbs)
HRWR	652 mL/100 kg (10 oz/100 lbs)	652 mL/100 kg (10 oz/100 lbs)	652 mL/100 kg (10 oz/100 lbs)
Slump	165 mm (6.5 in.)	165 mm (6.5 in.)	165 mm (6.5 in.)
Air content, %	6%	6%	6%
<b>% Length change (shrinkage) wet cure time, days</b>			
3 days	0.075	0.084	0.051
7 days	0.061	0.068	0.045
28 days	0.040	0.048	0.038

## Test Series 1: The Effect of Aggregate Type on Shrinkage of FORCE 10,000<sup>®</sup> Concrete

COARSE AGGREGATE TYPE	RIVER GRAVEL	CRUSHED LIMESTONE
Coarse aggregate	1090 kg	1837 lbs
Type II cement	332 kg	560 lbs
Class F fly ash	59 kg	100 lbs
FORCE 10,000 <sup>®</sup>	42.4 kg	71.5 lbs
HRWR	1174 mL/100 kg	18 oz/100 lbs
W/C + P ratio	0.35	0.35
Slump	102 mm	4 in.
Air content, %	2.0	2.0
% Length change, shrinkage, drying age (after 7 days wet cure)	River Gravel	Crushed Limestone
7 days	0.040	0.025
28 days	0.078	0.038
56 days	0.080	0.035
90 days	0.075	0.036

Note: Values do not represent all limestone and gravel aggregates.

## Test Series 2: The Effect of FORCE 10,000<sup>®</sup> on Shrinkage at Equal Paste Content

MIX DESCRIPTION	WITH FORCE 10,000 <sup>®</sup>		WITHOUT FORCE 10,000 <sup>®</sup>	
Units	SI	US	SI	US
Type II cement	332 kg	560 lbs	392 kg	600 lbs
Class F fly ash	59 kg	100 lbs	59 kg	100 lbs
FORCE 10,000 <sup>®</sup>	42.4 kg	71.5 lbs	0 kg	0 lbs
HRWR	1174 mL/100 kg	18 oz/100 lbs	1174 mL/100 kg	18 oz/100 lbs
W/C + P ratio	0.35	0.34		

Slump	127 mm	5 in.	127 mm	5 in.
Air content, %	3.0	3.0		
<b>% Length change, shrinkage, drying age (after 7 days wet cure)</b>	<b>with FORCE 10,000<sup>®</sup></b>		<b>without FORCE 10,000<sup>®</sup></b>	
7 days	0.040	0.038		
28 days	0.078	0.075		
56 days	0.080	0.079		
90 days	0.075	0.076		

### Test Series 3: The Effect of Curing on Shrinkage of FORCE 10,000<sup>®</sup> Concrete

MIX DESCRIPTION	MIDWEST GRAVEL	NORTHEAST GRAVEL	MIDWEST LIMESTONE
W/C + P ratio	0.37	0.37	0.37
FORCE 10,000 <sup>®</sup>	27.2 kg (46 lbs)	27.2 kg (46 lbs)	27.2 kg (46 lbs)
HRWR	652 mL/100 kg (10 oz/100 lbs)	652 mL/100 kg (10 oz/100 lbs)	652 mL/100 kg (10 oz/100 lbs)
Slump	165 mm (6.5 in.)	165 mm (6.5 in.)	165 mm (6.5 in.)
Air content, %	6%	6%	6%
<b>% Length change (shrinkage) wet cure time, days</b>			
3 days	0.075	0.084	0.051
7 days	0.061	0.068	0.045
28 days	0.040	0.048	0.038

## Conclusions

1. The type of aggregate used in the mix will influence the amount of shrinkage.
2. FORCE 10,000<sup>®</sup> has little effect on shrinkage when compared to concrete made without silica fume with equal paste content. ACI 234 indicates that the drying shrinkage of silica fume concrete is generally comparable to that of control concrete regardless of the water/cementitious ratio.

gcpat.com | North America Customer Service: +1 (877) 423 6491

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

FORCE 10,000 AND STRUX are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

In Canada, 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Suite 475, Alpharetta, GA 30009, USA

GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6

This document is only current as of the last updated date stated below and is valid only for use in the United States. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on [www.gcpat.com](http://www.gcpat.com). Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2024-06-21

[gcpat.com/solutions/products/force-10000-d-silica-fume/tb-0708-shrinkage-characteristics-force-10000-concrete](http://gcpat.com/solutions/products/force-10000-d-silica-fume/tb-0708-shrinkage-characteristics-force-10000-concrete)