

# TB-0910 — DCI® Results of FHWA Sponsored Corrosion Studies

---

/ concrete / mix design

## Introduction

This engineering bulletin discusses work done by Wiss, Janney & Elstner Assoc. (WJE) who examined the effectiveness of calcium nitrite corrosion inhibitor and other corrosion protection systems for protecting steel in concrete. The WJE research was sponsored by the Federal Highway Administration (FHWA) as well as members of private industry. Several conclusions were made as a result of this study, including:

- Lower water/cement ratio concrete is less permeable to chloride ions and delays the onset of steel corrosion in concrete.
- Although the corrosion of steel with 25 mm (1 in.) of clear concrete cover was greatly reduced because of calcium nitrite, more cover is essential.
- Calcium nitrite significantly reduces the severity of corrosion.

## Causes of Corrosion

In the alkaline environment provided by concrete, steel forms a protective ferric oxide layer. As chloride ions reach the steel surface, they attack the steel at flaws in this “passivating layer”, and initiate corrosion. As rust forms, the steel is weakened, and this expansive reaction causes stress inside the concrete. Cracks form at the reinforcement, and eventually, the concrete will crack and spall extensively.

In order to protect the reinforcement, several measures must be taken. Slowing the rate of chloride ingress delays the onset of corrosion. Chloride ions at the reinforcement at a concentration of 0.594 – 0.890 kg/m<sup>3</sup> (1.0 – 1.5 lbs/yd<sup>3</sup>) initiate corrosion. The time it takes for this amount of chloride to reach the steel depends on the concrete cover and the concrete permeability to chloride ions, which is affected by the water/cement ratio and concrete additives.

## The WJE Study

The FHWA hired WJE to run a series of tests to determine the effectiveness of corrosion protection systems. The results of these tests are reported in the FHWA report “Protective Systems for New Prestressed and Substructure Concrete”. In addition, members of private industry sponsored WJE as they continued these tests past the time required by the FHWA. The test procedures are briefly described on the following page.


Two different test procedures were run. The first included minidecks, pictured in Figure 1. Macrocell corrosion was measured by setting up a galvanic cell. Two pieces of rebar were cast near the top of the sample, and four pieces of rebar were cast near the bottom of the sample. A dike was built around the top surface of the sample and filled with saltwater. The chloride ions from the salt diffused through the concrete, reaching the upper mat of rebar. Since no chloride ions reached the lower mat during most of the test, these four rebars did not corrode. A galvanic cell was created by electrically connecting the upper and lower rebar mats, in order to increase the corrosion rate of the upper, or anodic, mat of steel.

For this test, water/cement ratios ranged from 0.32 to 0.50 and concrete cover ranged from 25 to 75 mm (1 to 3 in.). The FHWA sponsored the test for 48 weeks and WJE continued the testing for a total of 116 weeks.

Methods of monitoring corrosion were:

- Measuring the voltage across a resistor connecting the upper and lower mats, to calculate the macrocell corrosion current. The corrosion current is directly proportional to the corrosion rate.
- Measuring the macrocell driving voltage. This is measured immediately after uncoupling the top and bottom rebar mat. A higher driving voltage indicates a higher corrosion rate.
- Measuring the potential of the rebar with respect to a copper/copper sulfate half cell.

Figure 1



The most accurate method of measuring corrosion rates is monitoring the corrosion current. Although the macrocell corrosion current has limited accuracy, the parameters in this experiment are within those limitations. Chloride concentrations were also determined.

The second year-long study examined 19 full-size bridge members: cast-in-place columns and beams, and precast piles and deck panels. These specimens were subjected to various types of exposure to salt, designed to imitate the environments bridges are actually exposed to.

A water/cement ratio of 0.44 was used for all specimens. The cast-in-place concrete was moist-cured, while the precast members were heat-cured overnight. The same methods of monitoring corrosion were used as in the previous test.

## Test Results

The results of these two test programs confirmed many facts previously known or suspected. In each of the studies, an increase in the concrete cover over the steel extended the time it took for chloride ions to reach the reinforcement and, therefore, corrosion initiation.

During the first 48 weeks of testing minidecks, there was no corrosion of steel with at least 50 mm (2 in.) of cover. After 116 weeks some corrosion had begun in samples with 50 mm (2 in.) of cover without calcium nitrite protection ( $w/c = 0.50$ ).

As a result of these tests, the FHWA recommended increasing concrete cover to at least 55 mm (2 1/4 in.), in order to minimize the risk of early corrosion. These studies do not indicate that such concrete cover alone will provide adequate corrosion protection, but that it is an improvement over low, inadequate cover.

Lower water/cement ratios also decreased the rate of chloride ion diffusion through the concrete. As shown in Figure 2, the amount of chlorides at the rebar was lower, and the onset of corrosion was delayed in samples with lower water/cement ratios. As a result, the FHWA suggested that a ratio of no more than 0.44 be used. Many other studies have arrived at similar conclusions.

A microsilica (silica fume) admixture drastically reduced the ingress of chloride ions. The microsilica concrete specimen with 25 mm (1 in.) cover was corrosion-free. The study also notes a great increase in the concrete resistivity of the sample containing microsilica. A high resistivity may slow the rate of macrocell corrosion.

Along with samples tested for the FHWA, other conditions were examined by WJE for members of private industry. All of the water/cement ratios and concrete covers are listed in Table 1 for the plain concrete and concrete containing DCI<sup>®</sup> (calcium nitrite). Some of the minibeam were only tested for 48 weeks. The remainder were tested until they had been subjected to 116 weeks of cyclic ponding.

Concrete containing DCI<sup>®</sup> consistently outperformed concrete without DCI<sup>®</sup>.

Figure 2




Table 1 - Concrete Water/Cement Ratios and Rebar Cover for Samples Tested.

W/C	Cover		DCI <sup>®</sup>	
	mm	(in.)	L/M <sup>3</sup>	(gal/yd <sup>3</sup> )
0.50	25	(1)	0	(0)
0.50	25	(1)	20	(4)
0.50	25	(1)	30	(6)
0.40	25	(1)	0	(0)
0.40	25	(1)	20	(4)
0.32	25	(1)	0	(0)
0.32	25	(1)	20	(4)
0.50	50	(2)	0	(0)
0.50	50	(2)	10	(2)
0.50	50	(2)	20	(4)
0.40	50	(2)	0	(0)
0.40	50	(2)	20	(4)
0.32	50	(2)	0	(0)
0.32	50	(2)	20	(4)

The time at which corrosion began, and the severity of the corrosion were both affected by the presence of DCI®.

Under 25 mm (1 in.) of concrete cover, steel rebar began corroding after 6 weeks in 0.50 water/ cement ratio concrete. After 48 weeks of cyclic ponding, the minibeam had an average macrocell corrosion current of 225 microamps.

In DCI® concrete samples with the same cover and water/ cement ratio, the onset of corrosion was delayed. With a DCI® dosage of 20 L/m<sup>3</sup> (4 gal/yd<sup>3</sup>), samples showed signs of corrosion after 9.5 weeks (a 58% increase of the time to initiation). When DCI® was added at 30 L/m<sup>3</sup> (6 gal/yd<sup>3</sup>), corrosion began after 11 weeks of cyclic ponding (an 83% increase). The average macrocell corrosion current was 34 microamps, less than one-seventh that of plain concrete samples.

After 116 weeks of ponding, the corrosion potentials were -540 mV and -335 mV for plain and DCI® concrete respectively. All of these results are listed in Table 2.

The effectiveness of DCI® was confirmed in samples with lower water/cement ratios and 25 mm (1 in.) of cover. Steel in plain concrete with water/ cement ratios of 0.40 and 0.32 showed signs of corrosion after 5 and 2.5 weeks respectively.

In 0.40 water/cement ratio concrete, DCI® added at 20 L/m<sup>3</sup> (4 gal/yd<sup>3</sup>) delayed the onset to 21 weeks — a four-fold increase. The steel rebar in 0.32 w/c ratio concrete containing 20 L/m<sup>3</sup> (4 gal/yd<sup>3</sup>) of DCI® demonstrated no corrosion activity after 116 weeks. Other data is listed in Table 2.

The only sample with 50 mm (2 in.) of cover to show signs of corrosion during the test was a plain concrete minideck with a 0.50 w/c ratio. Other plain concrete samples with 50 mm (2 in.) of cover were not tested after 48 weeks of ponding.

The amounts of rust visible on the rebars are also listed in Table 2. A significant decrease in the steel rust is evident in concrete containing DCI® corrosion inhibitor. (Note that visual inspection of steel in plain concrete was conducted after only 48 weeks, while the steel in concrete containing calcium nitrite was inspected after 116 weeks). Other data, such as macrocell corrosion current and corrosion potential indicated relative rates of corrosion.

Based on the results of the first series of experiments, several corrosion protection systems were selected for further examination. Full-sized bridge members were made with both cast-in place and prestressed concrete. The water/cement ratio of the concrete was 0.44. Cover varied from 25 to 50 mm (1 to 2 in.) for gray steel; all other samples had 25 mm (1 in.) of cover.

In every instance, calcium nitrite inhibited the corrosion of the steel reinforcement. The corrosion rates and total corrosion of the steel was reduced tremendously by adding calcium nitrite to the mix. In cast-in- place columns, for example, the calcium nitrite controlled the corrosion rate of the reinforcement to one tenth that of steel in plain concrete.

Samples with more than 25 mm (1 in.) of cover did not corrode. By examining the profiles of chloride concentrations in the concrete, it is evident that at these depths, there is a relatively low chloride concentration. In heat-cured concrete, the ingress of chloride ions was slower than for cast-in-place concrete.

## Recommendations of Study

As a result of these tests and others, the FHWA developed several design considerations for bridge members. These included:

- The water-to-cement ratio should be as low as possible, preferably in the 0.32 to 0.44 range.
- Clear cover should be as large as possible, at least 55 mm (2 1/4 in.), in order to reduce the risk of early corrosion.
- Calcium nitrite offers effective corrosion inhibition and provides significant protection.
- A high-strength microsilica concrete mixture showed very good corrosion protection capabilities.

In addition, WJE came to the following conclusions, based on minideck tests that continued to 116 weeks for plain concrete and concrete containing calcium nitrite:

- A design with 50 mm (2 in.) cover and 10 to 20 L of DCI<sup>®</sup> /m<sup>3</sup> (2 to 4 gal of DCI<sup>®</sup> /yd<sup>3</sup>) of concrete is more realistic and economical than 25 mm (1 in.) cover and 20 to 30 L of DCI<sup>®</sup> /m<sup>3</sup> (4 to 6 gal of DCI<sup>®</sup> /yd<sup>3</sup>) of concrete.
- Calcium nitrite corrosion inhibitor is effective in controlling the corrosion of steel in concrete. Even at 25 mm (1 in.) of cover and a w/c of 0.50, calcium nitrite prolonged the time-to-corrosion of steel in concrete.

## Conclusions

In the experiments summarized here, DCI<sup>®</sup> calcium nitrite solution significantly delayed the onset of corrosion.

- In a 0.50 water/cement ratio concrete, the DCI<sup>®</sup> sample showed no signs of corrosion for a time period twice as long as in plain concrete [20 L of DCI<sup>®</sup> /m<sup>3</sup> (4 gal of DCI<sup>®</sup> /yd<sup>3</sup>) of concrete].
- In 0.40 water/cement ratio concrete, at the same dosage, steel in DCI<sup>®</sup> concrete did not begin to corrode for four times as long as in plain concrete.
- Once corrosion began, the rates were lower in concrete containing DCI<sup>®</sup>. Typically, the corrosion rate of steel in DCI<sup>®</sup> concrete was as little as one tenth that of steel in plain concrete.

Low water-to-cement ratio concrete, high concrete cover and heat-cured concrete extend the time before which corrosion of the steel rebar begins. However, in order for structures to achieve a long design life, additional corrosion protection is necessary. Calcium nitrite provides the protection needed to insure a long-lived, safe structure.

**gcpat.com | North America customer service: 1-877-4AD-MIX (1-877-423-6491)**

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

DCI<sup>®</sup> is a trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status. These products may be covered by patents or patents pending.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

In Canada, 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Suite 475, Alpharetta, GA 30009, USA  
GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6

This document is only current as of the last updated date stated below and is valid only for use in the United States. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on [www.gcpat.com](http://www.gcpat.com). Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2024-06-21

[gcpat.com/solutions/products/dci-corrosion-inhibitor/tb-0910-dci-results-fhwa-sponsored-corrosion-studies](http://gcpat.com/solutions/products/dci-corrosion-inhibitor/tb-0910-dci-results-fhwa-sponsored-corrosion-studies)