

TB-1601 — CLARENA® MC2000 Clay Mitigating Mid-Range Water Reducer Technical Bulletin

/ concrete / mix design


Introduction

CLARENA® MC2000 is a patented polycarboxylate (PC) based ASTM C494 Type A and F mid-range water reducer that is formulated with proprietary chemicals to provide best in class performance when used in concrete mixes containing a wide range of clay bearing aggregates. CLARENA® MC2000's robust dispersion capability in the presence of clay bearing aggregates results in consistent and predictable water reduction, excellent early and later age compressive strength, near neutral set times and superior finishability properties. CLARENA®MC2000 should be considered for use when moderate to high levels of clays are present in fine aggregates and laboratory and field test results confirm acceptable overall performance. CLARENA® MC2000 typical water reducer dosage rates range from 2-6 oz/cwt (130 to 391 mL/100 kg) and typical mid-range water reducer rates range from 7-15 oz/cwt (456 to 978 mL/100 kg).

Clay bearing fine aggregates, commonly found in the southwest region of the United States, can adversely affect the overall performance of primarily polycarboxylate based admixtures. Many clay minerals expand in the presence of water and can intercalate and absorb the polyalkylenes oxide component of PC based admixtures, thereby reducing cement dispersion and water reduction capabilities. This has recently become a more wide spread issue because several concrete industry trends have resulted in a decreased availability of high quality natural sands with growing dependence on typically higher clay content manufactured sands.

CLARENA® MC2000 is formulated with proprietary sacrificial agents that are absorbed and intercalate with clays before the PC component of the admixture. Therefore, CLARENA® MC2000 retains excellent, robust water reduction and other desirable properties at low dosage rates.

Extensive field testing using an array of commercially available cements, pozzolans and aggregates was conducted primarily in the Southwest region of the United States to evaluate overall CLARENA[®] MC2000 concrete performance. The first step of the field test protocol consisted of gathering and evaluating fine aggregates for clay content via a GCP modified methylene blue (MB) test procedure. This MB test procedure uses a colorimeter, which measures the absorbance of a given solution at specific light wavelengths. MB content is correlated to the light absorbed at a specific wavelength, thereby eliminating visual interpretation of the blue halo. A methylene blue value (MBV) is then calculated, with a higher MBV representing higher clay contents. Finally, MBV's are used to calculate % of clay contents for a particular fine aggregate sample. Clay contents less than 0.4% can be considered to be relatively low, while clay contents greater than 0.8% can be considered to be relatively high. Figure 1 below details % of clay contents for several fine aggregates that are currently commercially available in the U.S. and were utilized during CLARENA[®] MC2000 field testing. Typically, when clay contents are greater than 0.4%, slump (dosage) efficiency and the overall performance of polycarboxylate based admixtures can be adversely affected. Note all five of the higher clay content fine aggregates came from the southwest region (Arizona, New Mexico).



Two examples of field test results depicting typical CLARENA[®] MC2000 field performance are shown below.

Field Test 1 Arizona (Urban Ready-Mix plant)

Nine 4 cubic yard batches of concrete were batched and tested. As detailed in Table 1, three chemically distinct Mid-Range Water Reducers (DARACEM[®] 55, MIRA[®] 95, CLARENA[®] MC2000) were tested in triplicate, with all plastic and hardened data represented by averages of the 3 tests. Mix design specifics included 456 pcy (271 kg/ m³) Type I/II cement, 124 pcy (74 kg/m³) Type F fly ash, 970 pcy (576 kg/m³) #1 coarse aggregate, 820 pcy (487 kg/m³) 3/8" coarse aggregate, 1320 pcy (783 kg/ m³) fine aggregate and 300 pcy (178 kg/m³) water.

The fine aggregate sampled prior to field testing had MBV value of 1.00 mg/g and 0.44% clay, which is considered to be moderate, but relatively low for the SW region.

Field test results revealed MIRA[®]95 and CLARENA[®] MC2000 both performed well, compared to lignin based DARACEM[®] 55. Both MIRA[®] 95 and CLARENA[®] MC2000 had excellent slump (dosage) response, set time and 28 day compressive strengths properties. CLARENA[®] MC2000 had the best slump (dosage) response of the 3 admixtures tested.

Table 1 – Field Test 1 Test Data

Admixture Type (PC= polycarboxylate) (CM= clay mitigating)	Mid Range Water Reducer Dosage Rate		Slump				Dosage Response	W/C Ratio	Plastic Air Content	Initial Set Time	28 Day Compressive Strength		
			Before MRWR Added		After MRWR Added								
	(oz/cwt)	(mL/100kg)	(in)	(mm)	(in)	(mm)	(in)	(mm)	(%)	(hr:min)	(psi)	(MPa)	
1 - DARACEM 55 (lignin based MRWR)	11.3	736.8	3.1	78.7	6.9	175.3	3.8	96.5	0.52	2.1	4:55	5697	39.3
2 - MIRA 95 (PC based MRWR)	11.3	736.8	3.3	83.8	7.0	177	3.7	94.0	0.53	1.4	4:07	5993	41.3
3 - CLARENA CM2000 (PC + CM MRWR)	7.6	495.5	3.3	83.8	7.4	127.0	4.1	104.1	0.53	1.4	3:47	6057	41.8

Field Test 2 Arizona (Urban Ready-Mix plant)

Eight 4 cubic yard batches of concrete were batched and tested. As detailed in Table 2, three chemically distinct Mid-Range Water Reducers (DARACEM® 55, MIRA® 95, CLARENA® MC2000) were tested in duplicate, with all plastic and hardened data represented by averages of the 2 tests. Mix design specifics included 451 pcy (268 kg/m³) Type V cement, 113 pcy (67 kg/m³) Type F fly ash, 1800 pcy (1068 kg/m³) ASTM C-33 #1 coarse aggregate, 1310 pcy (777 kg/m³) fine aggregate and 290 pcy (172 kg/m³) water.

The fine aggregate sampled prior to field testing had MBV value of 1.95 mg/g and 0.85% clay, which is considered to be high, but typical for the SW region.

Field test results revealed all the mixes tested had fair slump (dosage) response. However, CLARENA® MC2000 showed significantly better slump (dosage) response, compared to lignosulfonate based DARACEM® 55 and PC based MIRA®95. Plastic air control, initial time of set and 28 day compressive strength were similar for all mixes tested.

Table 2 – Field Test 2 Test Data

Admixture Type (PC= polycarboxylate) (CM= clay mitigating)	Mid Range Water Reducer Dosage Rate		Slump				Dosage Response	W/C Ratio	Plastic Air Content	Initial Set Time	28 Day Compressive Strength		
			Before MRWR Added		After MRWR Added								
	(oz/cwt)	(mL/100kg)	(in)	(mm)	(in)	(mm)	(in)	(mm)	(%)	(hr:min)	(psi)	(MPa)	
1 - DARACEM 55 (lignin based MRWR)	11	717.2	3.1	78.7	4.3	109.2	1.2	30.5	0.53	1.3	3:25	3760	25.9
2 - MIRA 95 (PC based MRWR)	11	717.2	3	76.2	4.0	101.6	1	25.4	0.52	1.4	3:32	3840	26.5
3 - CLARENA CM2000 (PC + CM MRWR)	7.3	476.0	3.3	83.8	5	127.0	1.8	45.7	0.53	1.5	3:35	3780	26.1

In summary, field testing results showed CLARENA® MC2000’s robust dispersion capability in the presence of clay bearing aggregates resulted in consistent and predictable water reduction, excellent early and later age compressive strength, near neutral set times and superior finishability properties. CLARENA® MC2000 should be considered for use when moderate to high levels of clays are present in fine aggregates. It is always recommended laboratory and field testing be conducted to verify overall performance with specific sets of materials.

gcpat.com | North America Customer Service: +1 (877) 423 6491

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

CLARENA MC2000, DARACEM, and MIRA are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

In Canada, 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Suite 400, Alpharetta, GA 30009, USA

GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6

This document is only current as of the last updated date stated below and is valid only for use in the United States. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2023-06-28

gcpat.com/solutions/products/clarena-solutions-materials-management/tb-1601-clarena-mc2000-clay-mitigating