



CUT PURe

Product Description

Cut PURe is a hydrophobic polyurethane designed to fill large voids in rock fissures, gravel layers, joints, and cracks in concrete structures and for the cut-off of gushing water. Depending on the temperature and amount of accelerator (Cut Cat PURe) used, the grout quickly cures to a rigid, closed cell polyurethane foam that is resistant to most organic solvents, mild acids, alkali, petroleum and micro-organisms.

- P**hthalate free- no phthalate-based plasticizers
- U**nregulated for transport- no hazmat shipping
- R**eformulated TDI free-all MDI based technology.
- e**vironmentally friendly-NSF/ANSI 61 approved.



C US

CUT PURe when combined with CUT CAT PURe is certified by WQA to NSF/ANSI 61 for materials safety only, as verified and substantiated by test data. Please refer to WQA website (www.wqa.org) for use ratios and limitations.

Packaging & Handling

- Cut PURe: 5 gallon metal pail
50 gallon metal drum
- Cut Cat PURe: 32 oz. metal cans

Cut PURe is sealed under dry nitrogen because it is sensitive to moisture, and should be stored in original containers in a dry area.

Storage temperature must be between 40°F and 90°F. Once the packaging has been opened, the useful life of the material is greatly reduced and should be used as soon as possible.
Shelf life: 2 years.

Applications

- Sealing larger volume leaks through concrete cracks and fissures
- Filling voids
- Stabilizing soil or gravel

Product Advantages

- Free Foam Expansion up to 30 times
- Contains no volatile solvents
- Single Component
- Will not dilute in water
- Controlled reaction time
- 3 catalysts available: Cut Cat, Fast, XF

Properties

| Cut PURe Resin | | |
|----------------------|------------------------|------------------------|
| Solids | 100% | ASTM D2369 |
| Viscosity | 180 cps at 77 °F | ASTM D2196 |
| Color | Black-brown liquid | |
| Density | 1.10 g/cm ³ | ASTM D4659 |
| Flashpoint | 293 °F | ASTM D93 |
| Corrosiveness | Non-corrosive | |
| Cut Cat PURe | | |
| Viscosity | 15 cps at 77 °F | ASTM D2196 |
| Color | Red liquid | |
| Flashpoint | 158 °F | ASTM D93 |
| Cut PURe Cured | | |
| Density confined | 1.00 g/cm ³ | ASTM D3574 |
| Density free | 2 PCF | ASTM D3574 |
| Compressive strength | 35 to 4351 psi | Depends on confinement |

Reaction Times

| T | % Cat | End Reaction | Foam Factor |
|------|-------|--------------|-------------|
| 40°F | 5 | 5'35" | 22V |
| | 10 | 3'05" | 25V |
| 50°F | 5 | 5'00" | 24V |
| | 10 | 2'50" | 28V |
| 60°F | 5 | 4'45" | 25V |
| | 10 | 2'35" | 28V |
| 68°F | 5 | 4'35" | 27V |
| | 10 | 2'10" | 29V |
| 77°F | 5 | 4'00" | 28V |
| | 10 | 2'05" | 30V |
| 86°F | 5 | 3'35" | 29V |
| | 10 | 1'55" | 30V |
| 95°F | 5 | 2'55" | 29V |
| | 10 | 1'50" | 30V |

Limitations

Cut PRe must be used with Cut Cat PRe.

Low temperatures will significantly affect viscosity. If site temperatures are extremely low, heat bands or heated water baths may be used on the pails before and during installation to maintain the product's temperature. Avoid splashing water into open containers, as the material is water activated. Avoid exceeding 90°F when warming.

CAUTION: pH NOTICE. Water used to activate PRe Grouts must be in the pH range of 3-10 for optimum foam quality.

Installation Guidelines

Warning: Cut PRe must be used with Cut Cat PRe. Consult the Technical Data Sheets and SDS before using.

Installation Instructions: For detailed installation instructions refer to the DeNeef technical bulletin for your application.

Catalyst: Shake catalyst can 2-3 minutes. Pour the desired amount of Cut PRe into a clean dry pail. Measure the appropriate amount of Cut Cat PRe (refer to the **Reaction Times** section of this data sheet for the desired set time) and pour it into the pail. Stir until adequately mixed. Exceeding the recommended amount of catalyst may adversely affect the reaction and quality of the cured foam.

Injection: During injection the grout will follow the path of least resistance. When the material has stopped penetrating it will continue to expand against the limits of the confined space and compress within itself, forming a dense, closed cell foam.

Extreme conditions: For application procedures in extreme temperatures and specific environments or equipment recommendations call the DeNeef Technical Service Department.

Cleaning: Clean all tools and equipment which have been in contact with the resin with DeNeef Washing Agent before resin has cured. Products should be disposed of according to local, state, and federal laws.

Health and Safety

Always use protective clothing, gloves and goggles consistent with OSHA regulations. Avoid eye and skin contact. Do not ingest. Refer to SDS. **For emergencies, call CHEMTREC 1-800-424-9300.**

deneef.com | Technical Service: 1-713-896-0123

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

CUT and PRe are trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2016 GCP Applied Technologies Inc. All rights reserved.

GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140 USA.

In Canada, 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

GCP0083 DN-003-0616