

# ZYLA<sup>®</sup> 610

Water-reducing admixture -- ASTM C494 Type A and D

---

## Product Description

ZYLA<sup>®</sup>610 water-reducing admixture is a proprietary formulation incorporating highly purified specialty organic chemicals. ZYLA<sup>®</sup>610 promotes more complete hydration of Portland cement and has no effect on concrete air entrainment.

The ZYLA<sup>®</sup> product line of water reducers is specially formulated to have a synergistic effect with polycarboxylate-based mid-range and high-range water reducers that improve flat-work finishability. This product does not contain intentionally added chloride and as such is essentially chloride free. It is manufactured under rigid controls that provide uniform, predictable performance. ZYLA<sup>®</sup>610 is supplied as a light brown, low viscosity liquid and is ready-to-use as received. One gallon weighs approximately 9.1 lbs (1.1 kg/L).

## Product Advantages

- No impact on concrete air content
- Better control of water reduction and setting times as compared to traditional lignin-based water reducers
- Synergistic performance of polycarboxylate-based mid-range and high-range water reducers, which includes water reduction, concrete strength and air control
- In the hardened state, improves the compressive and flexural strengths at all ages of concrete versus traditional lignin-based water reducers

## Uses

ZYLA<sup>®</sup>610 is used to produce concrete mixes with lower water content (typically 3% to 10% reduction), greater plasticity and higher compressive strengths. ZYLA<sup>®</sup>610 is suitable for normal weight and light weight concrete in ready-mix, precast and prestressed applications.

## Finishability

The unique chemistry of ZYLA<sup>®</sup>610 positively impacts the finishability of concrete by providing a creamier and more homogenous texture, with more uniform bleed rate relative to traditional lignin-based water reducers. The influence of ZYLA<sup>®</sup>610 on the finishability of lean mixes has been particularly noticeable. Floating and troweling, by machine or hand, imparts a smooth, close tolerance surface.

## Addition Rates

The addition rate range of 3 to 5 fl oz/100 lbs (195 to 325 mL/ 100 kg) of cement or cementitious is typical for most applications. However addition rates of 2 to 7 fl oz/100 lbs (130 to 455 mL/100 kg) of cement or cementitious may be used if local testing shows acceptable performance. Pretesting is required to determine the appropriate addition rate for desired performance. The optimum addition rate depends on the other concrete mixture components, job conditions and desired performance characteristics.

## Compatibility with Other Admixtures and Batch Sequencing

ZYLA®610 is compatible with most GCP admixtures as long as they are added separately to the concrete mix, usually through the water holding tank discharge line. In general, it is recommended that ZYLA®610 be added to the concrete mix near the end of the batch sequence for optimum performance. Different sequencing may be used if local testing shows better performance. Please see GCP Technical Bulletin TB-0110, *Admixture Dispenser Discharge Line Location and Sequencing for Concrete Batching Operations* for further recommendations.

Pretesting of the concrete mix should be performed before use, as conditions and materials change in order to assure compatibility, and to optimize dosage rates, addition times in the batch sequencing and concrete performance. For concrete that requires air entrainment, the use of an ASTM C260 air-entraining agent (such as Daravair® or Darex® product lines) is recommended to provide suitable air void parameters for freeze-thaw resistance. Please consult your GCP Applied Technologies representative for guidance.

## Packaging & Handling

ZYLA®610 is available in bulk, delivered by metered tank trucks, in totes, and in drums.

ZYLA®610 will freeze at about 23.7°F (-4.6°C), but will be completely uniform after thawing and thorough agitation.

## Dispensing Equipment

A complete line of accurate, automatic dispensing equipment is available. ZYLA®610 may be introduced to the concrete mix through the water holding tank discharge line. The ZYLA® product line is formulated to be free of sediment.

## Specifications

Concrete shall be designed in accordance with *Standard Recommended Practice for Selecting Proportions for Concrete*, ACI 211. The water-reducing admixture shall be ZYLA®610, as manufactured by GCP Applied Technologies, or equal. The admixture shall not contain calcium chloride as a functional ingredient. ZYLA®610 will not promote corrosion of reinforcing steel embedded in concrete. It shall be used in strict accordance with the manufacturers' recommendations. The admixture shall comply with ASTM Designation C494, Type A water reducing and Type D water reducing and retarding admixtures. Certification of compliance shall be made available on request.

The admixture shall be delivered as a ready-to-use liquid product and shall require no mixing at the batching plant or job site.

[gcpat.com](http://gcpat.com) | North America Customer Service: 1 877-4AD-MIX1 (1 877-423-6491)

This product or its use may be covered by US Patent Nos. 7,462,236.

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

ZYLA, Daravair and Darex are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140 USA.

In Canada, 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

This document is only current as of the last updated date stated below and is valid only for use in the United States. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on [www.gcpat.com](http://www.gcpat.com). Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2019-03-13

[gcpat.com/solutions/products/zyla-water-reducing-admixtures/zyla-610](http://gcpat.com/solutions/products/zyla-water-reducing-admixtures/zyla-610)