

CBP™ 2

Admixture for Low Slump Concrete Products

Product Description

CBP™ 2 is a high performance ready-to-use liquid admixture recommended for use in the production of very low or zero-slump concrete. CBP 2 is supplied ready-to-use, the ingredients are premixed in exact proportions under strict quality control to provide uniform results. One Liter weighs approximately 1.01 kg (1 gallon weighs approximately 8.4 lbs).

Uses

CBP 2 may be used in all zero or low slump concretes to increase workability while retaining cohesiveness and providing more complete cement hydration. Zero or low slump concrete mixes are characteristically dry, containing only sufficient water for cement hydration. An increase in water content, while desirable to improve workability, would be impractical, from a production standpoint, in applications where a very low or zero slump concrete is necessary. As a dispersing agent, CBP 2 will compensate for the water deficiencies in such mixes thereby improving the workability, dispersing the cement for more complete hydration, and consequently producing greater strengths for a given cement content.

Application Information

Addition Rates:

The typical addition rate of CBP 2 is 130–450 mL/100 kg (2–7 fl oz /100 lbs) of cementitious materials in the mix. The optimal addition rate will depend on the concrete materials, job conditions and desired performance characteristics.

Compatibility:

CBP 2 should not be premixed with other admixtures. The performance of the admixture will be affected by the presence of other chemicals. Testing should be performed to confirm compatibility with other admixtures.

Dispensing:

A complete line of accurate, automatic dispensing equipment is available. CBP 2 may be introduced at any time during the mixing cycle but not directly onto the cement.

Product Advantages

- Improves compaction
- Increases compressive strength
- Reduces culls
- Produces sharper corners and edges
- Faster cycling times

Packaging:

CBP 2 is available in drums and mini-bulk containers.

Health & Safety:

All precautions defined on the SDS (Safety Data Sheet) for CBP 2 must be followed.

Storage:

CBP 2 will freeze at about -1°C (30°F), but it will return to full effectiveness after thorough thawing and mechanical agitation.

gcpat.com | North America Customer Service: 1 877-4AD-MIX1 (1 877-423-6491)

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

CBP 2 is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140 USA.

In Canada, 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

This document is only current as of the last updated date stated below and is valid only for use in the United States. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on www.gcpat.com. Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2018-08-24

gcpat.com/solutions/products/cbp-2