

# MONOKOTE<sup>®</sup> FIREPROTECT<sup>™</sup> Product Data Sheet

## Product Description

Monokote<sup>®</sup> FireProtect<sup>™</sup> is a rigid mineral wool board designed to deliver fire resistance, thermal insulation, and acoustical management within a single integrated product. Monokote<sup>®</sup> FireProtect<sup>™</sup> is engineered to meet stringent fire resistance requirements for steel structures, offering robust fire protection with ease of installation. Monokote<sup>®</sup> FireProtect<sup>™</sup> is ideal for commercial, industrial, and data center projects. It can be installed quickly at any stage of construction, no matter the roof traffic, temperature, or condition of the substrate.

Monokote<sup>®</sup> FireProtect<sup>™</sup> is available in multiple thicknesses: ¾, 1, 1 ¼, 1 ½, 2, 2 ¾, 3 ¼, 4 in (20, 25, 30, 40, 50, 60, 80, 100mm)

## Product Advantages

- UL-tested and compliant with ASTM E119 / CAN ULC S101 for columns, beams, floor/ceiling, and roof/ceiling assemblies.
- Fully loaded to 50 ksi fire tests on joists, beams and decking, with a range of tested sizes.
- Designed for dry and rapid installation without disruption to other trades.
- Installs dry without steel surface preparation or specialized equipment; compatible with primed and painted steel substrates.
- Suitable for interior and exterior applications with weather exposure during construction.
- Non-combustible, non-flammable, and asbestos-free.
- VOC Emissions and Content reports available.
- High R- and Noise Reduction Coefficient (NRC)- values.
- Comprised of 70% recycled material.

## System Components

Rigid mineral wool board; accessories include Monokote<sup>®</sup> FireProtect<sup>™</sup> pigtail screws for fastening, Monokote<sup>®</sup> FireProtect<sup>™</sup> Noggins for beams and columns, and Monokote<sup>®</sup> Flute Fillers for deck applications.

## Dimensions and Packaging

Board: 47 ¼ L x 39 ¾ W; Thicknesses: ¾-4 in (20-100mm); Density: 10 pcf (~150 kg/m<sup>3</sup>); Supplied on wooden pallets, stacked or packaged; accessories packaged in labeled boxes.

## Installation

Monokote<sup>®</sup> FireProtect™ is supplied in a standard board size 47 ¼ L x 39 ⅜ W (1200mm x 1000mm) with thicknesses ranging from ¾-4 in (20–100mm), palletized and shrink- wrapped. The board can be cut using a table/hand saw or knife. Noggings 4" (100mm) wide x 1 ⅝" (40mm) minimum thickness are cut to fit tightly between the flanges 24" on center. For deck applications it is fastened directly to the deck using standard deck screws.

Monokote<sup>®</sup> FireProtect™ is cut and installed to box the steel and is held in place with Monokote<sup>®</sup> FireProtect™ Screws at 6" on center. Refer to the UL Fire Resistance directory for the UL Designs and details. Please refer to our field Installation manual for specific design and application details.

## Technical Properties

Air Erosion	ASTM E859	0.00g at 5800 ft / min
Deflection	ASTM E759	No deflection
Tensile Strength	ASTM C209	14.6 psi
Density	ASTM E605	10.0 pcf (161 kg/m3)
Compressive Strength (10% deformation)	ASTM C165	3.45 psi
Thermal Performance (R-value)	ASTM C158	4.5 per inch
Sound Absorption (NRC)	ASTM C423	0.9
Fungal Resistance	ASTM C1338	No growth
Surface Burning Characteristics (Flame Spread / Smoke Development)	ASTM E84	0 / 0 (Class A)
Surface Burning Characteristics (Flame Spread / Smoke Development)	ULC CAN S101	5/0 (Class A)
Combustibility	ASTM E1354 ASTM E136	Non-combustible

North America customer service: 1-877-4AD-MIX (1-877-423-6491)

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Suite 400, Alpharetta, GA 30009, USA  
GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6

This document is only current as of the last updated date stated below and is valid only for use in the United States. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on [www.gcpat.com](http://www.gcpat.com). Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2026-06-03

[prod-gcpat-com.content.saint-gobain.io/solutions/products/monokote-fireprotect/monokote-fireprotect-product-data-sheet](http://prod-gcpat-com.content.saint-gobain.io/solutions/products/monokote-fireprotect/monokote-fireprotect-product-data-sheet)