

# OPTEC<sup>®</sup> Paver Enhancer

Multi-functional efflorescence control admixture

---

## Product Description

OPTEC<sup>®</sup>Paver Enhancer admixture is an innovative admixture specifically formulated to enhance the physical properties and overall appearance of concrete pavers and Segmental Retaining Wall (SRW) units. OPTEC<sup>®</sup>Paver Enhancer can enhance color dispersion and help minimize secondary efflorescence. It provides excellent mix plasticity for improved physical attributes and machinability. OPTEC Paver Enhancer is supplied as ready-to-use liquid. OPTEC<sup>®</sup> Paver Enhancer provides a medium swipe on the surface of the unit for better water control.

## Product Uses

OPTEC<sup>®</sup>Paver Enhancer may be used in concrete pavers, segmental retaining wall units and other low slump concrete products where improved physical properties and aesthetics are desired. OPTEC<sup>®</sup>Paver Enhancer is designed to reduce secondary efflorescence, provide improved machinability and unit physical properties.

A full line of companion products are available to provide additional qualities such as, primary efflorescence control, acceleration and densification.

## Product Advantages

- Improves cement and pigment dispersion
- Cement and pigment reduction potential
- Improves compressive strength
- Minimizes secondary efflorescence
- Decreases cycle time
- Increases density
- Lowers absorption

## Product Function

OPTEC<sup>®</sup>Paver Enhancer admixture improves the dispersion of the cement throughout the mix resulting in better cement hydration and thus higher early and ultimate compressive strengths. Through this dispersion action, cement and consequently pigment, reductions are possible (testing is recommended to determine cement reduction potential). OPTEC<sup>®</sup>Paver Enhancer may also allow for increased water in the mix, which also promotes greater cement hydration.

OPTEC<sup>®</sup>Paver Enhancer may be used to increase the density or lower the absorption if desired. OPTEC<sup>®</sup>Paver Enhancer also improves the plasticity of the mix for improved machinability and reduced cycle times.

## Application Information

### Addition Rates

OPTEC®Paver Enhancer is generally used at a rate of 6–12 oz/cwt (390–780 mL/100 kg) of cementitious materials including, fly ash and other pozzolans. The addition rate is dependent upon the specific set of materials and the desired end properties.

### Mixing Procedure

OPTEC® Paver Enhancer is compatible with most concrete admixtures. However, when multiple admixtures are used they must be added separately to the concrete.

OPTEC®Paver Enhancer should be added separately to the mix after the initial wetting of the cement and before or with the addition of the final mix water. Once OPTEC®Paver Enhancer is batched, it should be mixed for a minimum of one minute, but preferably two minutes. Mix times of less than one minute should be avoided. Never add OPTEC®Paver Enhancer to dry cement.

Variables such as cementitious content, aggregate gradations, processing equipment, and curing conditions may have an impact on the effectiveness of OPTEC®Paver Enhancer. Testing with local materials and production equipment is necessary to determine the end results.

Consult your GCP representative for more information.

## Dispensing Equipment

OPTEC®Paver Enhancer can be dispensed using conventional air diaphragm pump systems. For further information, contact your local GCP representative.

## Packaging

OPTEC®Paver Enhancer admixture is available in drums and returnable totes.

## Health & Safety

All precautions defined on the SDS (Safety Data Sheet) for OPTEC®Paver Enhancer must be followed.

## Storage

OPTEC®Paver Enhancer must be protected from freezing at temperatures of 32 °F (0 °C) and below, as the admixture is not usable once frozen.

gcpat.com | North America Customer Service: 1 877-4AD-MIX1 (1 877-423-6491)

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

OPTEC is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2018 GCP Applied Technologies Inc. All rights reserved.

GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140 USA.

In Canada, 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6.

This document is only current as of the last updated date stated below and is valid only for use in the United States. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on [www.gcpat.com](http://www.gcpat.com). Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2021-02-05

[gcpat.com/solutions/products/masonry-hardscape-solutions/optec-paver-enhancer](http://gcpat.com/solutions/products/masonry-hardscape-solutions/optec-paver-enhancer)