

# SAFETRACK<sup>®</sup> DS Data Sheet

Premium Traffic Coating

---

## Product Description

SAFETRACK<sup>®</sup> DS is a rapidly curing, liquid applied waterproofing and surfacing system designed specifically for parking garage applications. Utilizing GCP's advanced ESSELAC<sup>®</sup> technology, the system is comprised of a tough, impermeable waterproofing membrane and a fully compatible, durable skid resistant surface finish.

The system may be partially or fully reinforced subject to the design of the area being treated. SAFETRACK<sup>®</sup> DS is suitable for both new construction and refurbishment construction.

## Uses

SAFETRACK<sup>®</sup> DS is designed to protect structures from water penetration and corrosion whilst providing skid resistant properties in a variety of trafficked applications including:

- Parking garages
- Pedestrian walkways and footbridges
- Balconies and exposed decks

## Features

- 100% seamless waterproofing featuring ESSELAC<sup>®</sup> technology
- Rapid cure at low temperatures, installs down to 23 °F
- Excellent abrasion and chemical resistance
- Lightweight and flexible
- Durable skid resistant surface
- Trafficable within one hour

## Surface Preparation

The success of any waterproofing system is dependent on the thoroughness of the surface preparation.

All concrete decks must be prepared by suitable mechanical means to provide a sound surface. All laitance should be removed so that the aggregate in the deck slab is visible. Water jetting is not an acceptable method of preparation.

New concrete decks must be a minimum of fourteen days old. The substrate must be clean, dry and structurally sound. It must be free from laitance, oils and other surface contaminants.

For substrates other than concrete or where additives, cement replacement or curing compounds have been used, contact GCP to obtain approval for the use of the system.

## Application

### Primer

Concrete substrates must be primed using PAR1 Primer prior to application of the membrane. Apply using a brush or roller.

### Membrane

The SAFETRACK<sup>®</sup> DS Membrane is metered, mixed and spray applied using plural component spray equipment.

### Wearing Course

The SAFETRACK<sup>®</sup> DS Wearing Course is poured onto the membrane and spread out using a notched squeegee. This is then followed over with a medium pile roller to achieve the desired surface finish.

The wearing course should be applied to horizontal surfaces in one coat at a minimum coverage of 32ft<sup>2</sup>/gal for a nominal dry film thickness of 50 mils with a minimum of 40 mils. To the vertical surfaces it must be applied in two coats. Each coat on the vertical surface should be applied to give a minimum dry film thickness of 20 mils.

The system can be trafficked once the wearing course has cured, typically within 1 hour.

It is essential that good air circulation and ventilation be provided during application in enclosed spaces to ensure full cure.

## Technical Data

PROPERTY	VALUE
Application Temperature Range	23 to 95°F
<b>Minimum Overcoating Times</b>	
<b>PAR1 Primer</b>	
85°F	15 minutes
50°F	30 minutes
32°F	45 minutes
<b>Membrane</b>	
85°F	45 minutes
50°F	90 minutes
32°F	2 hours
<b>Wearing Course</b>	
85°F	20 minutes
50°F	50 minutes
32°F	60 minutes

## Packaging and Storage

PAR1 Primer 4.7 gal kits

SAFETRACK® DS Membrane 93.4 gal kits (2 x 46.7 gal drums)

SAFETRACK® DS Wearing Course 27.5kg Kits

All components of the SAFETRACK® DS System should be stored in cool, dry, protected conditions, out of direct sunlight and in accordance with the relevant site Health & Safety regulations. Storage temperature must not exceed 68°F. Do not store near open flames or foodstuffs.

Stored in unopened containers, under the correct conditions, the components have a shelf life of six months.

## Cleaning

All tools and equipment should be cleaned with acetone before the material is allowed to cure.

## General Information

SAFETRACK® DS is part of a wide range of specialist waterproofing surfacing and repair materials manufactured and supplied by GCP Applied Technologies.

## Health & Safety

Users must read and understand the product label and Safety Data Sheet for each system component before use. All users should acquaint themselves with this information prior to working with the material. Carefully read detailed precaution statements on the product labels and SDS before use. SDS's can be obtained from the GCP web site at [gcpat.com](http://gcpat.com) or by contacting GCP toll free at 1-866-333-3SBM (3726).

## Physical Properties (SAFETRACK<sup>®</sup> DS Membrane)

Property	Test Method	Result
Application Temperature		23 °F to 95 °F
System thickness (typical dry film)	Wearing Course Only	Min. 55 mils (including primer)
	Un-reinforced	145 mils
	Reinforced	180 mils
Gel Time	Internal	6-11 minutes @ 68 °F (20 °C)
Overcoating Time	Internal	45 minutes @ 68 °F (20 °C)
Tensile Strength (typical)	ASTM A412	1,400 psi
Elongation At Break (typical)	ASTM A412	135%
Tear Strength	ASTM D624	300 lbf/in
Dynamic Crack Bridging	ASTM C1305	
@ 1/8 in (3.2 mm), -15 °F (- 26 °C)	(10 cycles)	Pass
Tensile Bond Strength (minimum)		
Concrete	ASTM D4541-89	100psi
Steel	ASTM D4541-89	>250 psi
Heat aging	ASTM C1522	Pass
Shore A	ASTM D2240	60

[gcpat.com](http://gcpat.com) | North America customer service: 1-866-333-3726

GCP also provides a wide range of polymer overlays, high friction surfacing, pavement marking and color demarcation systems for highways and private use. Please contact us for further information.

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation or suggestion is intended for any use that would infringe any patent, copyright or other third-party right.

ESSELAC and SAFETRACK are trademarks, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2023 GCP Applied Technologies, Inc. All rights reserved.

Printed materials intended for use in the United States only

GCP Applied Technologies, 20 Moores Road, Malvern, PA 19355, USA.  
GCP Canada, Inc., 294 Clements Road, West, Ajax, Ontario, Canada L1S 3C6

This document is only current as of the last updated date stated below and is valid only for use in the United States. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on [www.gcpat.com](http://www.gcpat.com). Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2026-06-23

[gcpat.com/solutions/products/safetrack-road-maintenance-products/safetrack-ds-cold-applied-waterproofing-wearing-and-traffic-coating/safetrack-ds](http://gcpat.com/solutions/products/safetrack-road-maintenance-products/safetrack-ds-cold-applied-waterproofing-wearing-and-traffic-coating/safetrack-ds)